

# DuPont Performance Coatings

## Color Formula Inquiry Report

From	SANDRA SAID	Date	Nov 29, 2009
------	-------------	------	--------------

<b>Formula Standard #</b>	837074	<b>Years Used</b>	2009 - 2009
<b>EU Stock # / Alt #</b>	Q7351 / 1	<b>Lead (Pb) Free</b>	Y
<b>Color Name</b>	SAKANA	<b>PCP</b>	N
<b>Formula Owner Region</b>	AUSTRALIA	<b>Quality</b>	6000 CENTARI 6000
<b>Formulation Date</b>	Nov 23, 2009	<b>Value Shade</b>	4
<b>Coat</b>	BASECOAT	<b>Paint Code</b>	TOYOTA 6T1
<b>EU Alt Color Change</b>			
<b>Color Owner</b>	ANZ SERVICE MATCHES		
<b>Asia Color Variance</b>			

### Ingredients

**Quantity To Mix** 1.0LTR (100% Fill)

**Display Units** GRAMS

Ingredient	Ingr Quality	Description	Amount	Accum. Amount
AM11		MEDIUM ALUMINUM	150.7	150.7
4530S		FLOP CONTR AGENT	59.8	210.5
AM3		CRYSTALLINE FROST	25.5	236.0
AM5		JET BLACK	23.0	259.0
AM31		FAST GREEN L.S.	22.1	281.1
AM2		WHITE L.S.	6.7	287.8
AM90		TRANSOXIDE YELLOW	5.5	293.3
AM70		FAST BLUE L.S.	3.4	296.7
XB155		M.S. BINDER	311.9	608.6
XB165		M.S. BINDER	353.8	962.4

### Messages

**Language** ALL

**Region**

Code	Region	Language	Text
------	--------	----------	------