





























DuPont Refinish  
More than just paint ...

# Low Emission 2K Non Sanding

<b>3920S Degreaser</b>  3920S-8 - GB		 <p>Eliminates non-water soluble contaminants from prepared areas to obtain a perfectly cleaned surface before the application of a primer or topcoat.</p>										
<b>635R Etching Primer</b>  635R-6 - GB		       <table border="1" data-bbox="582 630 683 686"> <thead> <tr> <th>Vol</th> <th>Wt</th> </tr> </thead> <tbody> <tr> <td>635R 1</td> <td>100</td> </tr> <tr> <td>636R 1</td> <td>90</td> </tr> </tbody> </table> <p>DIN 4: 16-23 sec</p> <p>8 hr in non-metallic container</p> <p>Compliant Guns (HVLP / HTE) Gravity feed 1.2-1.4 mm Suction feed 1.4-1.6 mm Pressure feed 1.0-1.2 mm</p> <p>1</p> <p>30min - 48 hr before recoating</p> <p>do no tuse if relative hum. &gt;80%</p>	Vol	Wt	635R 1	100	636R 1	90				
Vol	Wt											
635R 1	100											
636R 1	90											
<b>LE2001/4/7 Low Emission Primer Plus Non Sanding (XK)</b>  LE2004-11 - GB		      <table border="1" data-bbox="582 845 683 917"> <thead> <tr> <th>Vol</th> <th>Wt</th> </tr> </thead> <tbody> <tr> <td>LE2001-4-7 4</td> <td>100</td> </tr> <tr> <td>XK205-6 1</td> <td>18</td> </tr> <tr> <td>LE2031-2 3</td> <td>45</td> </tr> </tbody> </table> <p>DIN 4: 14-16 s</p> <p>XK205: 1.30 - 2.30 hr XK206: 2 - 3 hr</p> <p>Compliant guns (HVLP / HTE) Gravity feed 1.4-1.6 mm Suction feed 1.6-1.8 mm Pressure feed 1.0-1.2 mm</p> <p>1</p> <p>Single Stage: 15 min till 8 hr Centari 600/6000: 15 - 45 min</p>	Vol	Wt	LE2001-4-7 4	100	XK205-6 1	18	LE2031-2 3	45		
Vol	Wt											
LE2001-4-7 4	100											
XK205-6 1	18											
LE2031-2 3	45											
<b>C5035 Low Emission 2K Topcoat</b>  C5035-12 - GB		        <table border="1" data-bbox="582 1069 683 1157"> <thead> <tr> <th>Vol</th> <th>Wt</th> </tr> </thead> <tbody> <tr> <td>Centari 5035 3</td> <td>-</td> </tr> <tr> <td>XK203 1</td> <td>-</td> </tr> <tr> <td>XK205 -</td> <td>-</td> </tr> <tr> <td>XK206 -</td> <td>-</td> </tr> </tbody> </table> <p>DIN 4: 19-24s</p> <p>XK203 45min. XK205 1h XK206 2h</p> <p>Compliant Guns (HVLP / HTE) Gravity feed 1.3-1.5 mm Suction feed 1.5-1.8 mm Pressure feed 1.0-1.2 mm</p> <p>2</p> <p>Poor hider colors 5min. between coats Good hider colors 0-3min.between coats</p> <p>XK203 20°C 3h XK205 4h XK206 60°C 20min. 30min. 40m.+ 1hr airdry</p> <p>Flash time 10min. Distance 80cms Half power 5min. Full power 10min.</p>	Vol	Wt	Centari 5035 3	-	XK203 1	-	XK205 -	-	XK206 -	-
Vol	Wt											
Centari 5035 3	-											
XK203 1	-											
XK205 -	-											
XK206 -	-											